# PHOTOCURE GT

Water and solvent Resistant SBQ Direct Emulsion

# **Features/Application**

- Able to use as it is, but adding diazo will improve resolution and impression.
- Fast Exposure time, faster screen turnaround for volume production
- High solid contents and viscosity for easy coating and build up emulsion thickness
- Suitable for texile application for water-based ink, HSA ink and solvent cleaning
- Excellent resolution and definition
- Easy to reclaim

## **Specifications**

- Viscosity: Approx. 14,000mPa·s(25°C)
- Solid Contents: Approx. 43%
- Packaging Standards:1kg, 5kgs, 200kgs
  \*\*Contact us for custom packaging.

## **Exposure Data**

| Screen mesh, Color              | EOM (µm)                              | Metal Halide Lamp*<br>LED 405nm** |
|---------------------------------|---------------------------------------|-----------------------------------|
| Polyester 31mesh/cm-100φ White  | 20µm<br>Print side 2/Squeegee side 2  | 240 ~ 360 mJ<br>120 ~ 180 mJ      |
| Polyester 31mesh/cm-100φ White  | 140µm<br>Print side 2/Squeegee side 8 | 450 ~ 550 mJ<br>230 ~ 280 mJ      |
| Polyester 59mesh/cm-48φ White   | 10µm<br>Print side 1/Squeegee side 1  | 120 ~ 180 mJ<br>60 ~ 90 mJ        |
| Polyester 59mesh/cm-48φ White   | 20µm<br>Print side 1/Squeegee side 2  | 180 ~ 300 mJ<br>90 ~ 150 mJ       |
| Polyester 100mesh/cm-40φ Yellow | 10μm<br>Print side 2/Squeegee side 2  | 120 ~ 180 mJ<br>60 ~ 90 mJ        |

The above is for guideline purposes only. Please use a grayscale exposure calculator to identify optimal exposure time. If you add diazo 1g/kg, please expose 1.5 times as a guide.



 5-3-10 Yokokawa, Sumida-ku, Tokyo Japan URL http://www.murakami.co.jp/english/

## **Instructions**

- · Use Murakami MSP cleanser to remove excess grease on mesh.
- Dissolve provided diazo with 2% water of emulsion volume.
  Please do not use warm water.
- Prior to use, let mixed emulsions settle for one day.
  Or for immediate use, filter it with 100/cm or higher.
- · Coat slowly to minimize air contamination.
- · Dry out the coated screen by faned warm air at 40°C. (104°F)

#### [Remarks]

- · Please filterate emulsion by mesh fabric for interval use.
- · Please handle emulsion gently because of high sensitive emulsion.
- · Keep the mixed emulsion in a cool and UV light safe area and use it within 1 week.
- · Wearing protective equipment is required. Please confirm SDS for more details.
- To avoid the deterioration of screen,
  please be caution for the use of ink and detergent containing the solvents mentioned below.
  - \* N-Methyl Pyrrolidone(NMP)
  - \* N,N-dimethylformamide
  - \* Methanol
  - \* Ethanol
  - \* Ethylene Glycol
  - \* Propylene Glycol

#### **Pictures**





